
Delta

FYT
FIJAMOS EL MUNDO

30113055 DELTA-FYT DK3 5,5

Material	Acero AISI 1022	Diámetro (mm.)		5,5
Tratamiento térmico	Austenitización + Temple + Revenido	Capacidad de taladro		4 mm.
Protección corrosión	Recubrimiento Delta tone	Dureza	Superficial	Min 560 HV
Longitudes (mm.)	25		Núcleo	240 - 425 HV
Fallo de rotura frente a esfuerzo cortante	10.000 N	Fallo de rotura frente a Tracción		16.000 N



Fuerza máxima de arrancamiento (N)*

Espesor (mm.)	2,00	3,00	4,00	5,00
Fuerza (N)	3.400	6.300	9.300	11.500

*. Valor medio de ensayo.




Fuerza máxima de pullover (N)*

Espesor (mm.)	0,50	0,60	0,70	0,80	1,00
Sin arandela (N)	840	1.008	1.176	1.344	1.680
Arandela P 16 (N)	1.120	1.344	1.568	1.792	2.240
Arandela P 18 (N)	1.260	1.512	1.764	2.016	2.520

*. Valores obtenidos a partir de la instrucción del acero estructural para una chapa ST37 (350 N/mm2)







Fuerza Cortante máxima (N)

Espesor (mm.)	0,63	0,75	1,00	1,00	1,50	1,50
Perfil (mm.)	2,00	3,00	2,00	3,00	2,00	3,00
Fuerza (N)	3.500	5.400	6.800	7.300	10.000	10.000

*. Valores obtenidos a partir de la instrucción del acero estructural para una chapa ST37 (350 N/mm2)

30113055 DELTA-FYT DK3 5,5

FYT
FIJAMOS EL MUNDO

Los valores de la gráfica[1] son valores medios de ensayo (ẋ) Se recomienda aplicar los siguientes coeficientes según norma CEN-TS 17659:

Table 2 - Recommended material partial (safety) factors for fastening in structural decks of different marterials

Material of structural deck	Nominal thickness	Characteristics [a]	γM
Steel according to EN 10346	0,50 ≤ t < 0,70 mm	yield strength ≥ 280 N/mm^2	2,0
	t ≥ 0,70 mm	yield strength ≥ 280 N/mm^2	1,8
Aluminium according to EN 485	t ≥ 0,70 mm	yield strength ≥ 195 N/mm^2	2,0 [b]
Concrete according to EN 206		Minimum C12/15	2,1 [c]
Light weight concrete according to EN 12602		≥ 500 kg/m^3	3,0 [b]

Material of structural deck	Nominal thickness	Characteristics [a]	γM
Wood - soft wood according to EN 338	t ≥ 20 mm	Minimum C24	1,86 [d]
OSB according to EN 300	t ≥ 18 mm	Minimum OSC/3	1,86 [d]
Plywood according to EN 636	t ≥ 18 mm	Minimum Service class 2 (EN 1995-1-1) Intended application = Structural S	1,86 [d]

a. Recommended for new structural decks.
b. This recommended value is based on hnowledge / experience.
c. This value is based on γ_{inst} = 1,4.
d. γM is the total safety based on κ_{mod} = 0,7 according EC 5.

Ejemplo del cáculo de resistencia de las fijaciones:

Datos: Correa Acero 4 mm / Chapa 0,7 mm / con tornillo FYT DK3 5,5 CE Con arandela 16



1. Resistencia a tracción:
   - Según valores de la ficha técnica:
     W_{test} = 9.300 N/Fijación
   - Aplicamos coeficiente minoración 90 %:
     W_{char} = 8.370 N/Fijación
   - Aplicamos coeficiente de seguridad:
     W_{adm} = 4.185 N/Fijación
2. Resistencia a pull-over:
   - Según valores de la ficha técnica:
     W_{adm} = 1.568 N/Fijación

Se utiliza el menor de estos valores

Valor de diseño de las fijaciones: W_{adm} = 1.568 N/Fijación.



Protección al fuego · Viga laminado en Frio · Tornillo Autotaladrante · Cabeza Hexagonal