
FIJAMOS EL MUNDO

02163N35 i-FYT DK3N 3,5

Material	AISI 304 stainless steel		Diameter (mm)	3,5
Heat treatment	Not hardened		Drilling capacity	2.5 mm aluminium
Corrosion protection	A2 stainless steel	Hardness	Surface	-
Lengths (mm)	13 - 50		Core	-
Shear failure load	3.750 N		Tensile failure load	6.250 N



Maximum pull-out force in aluminium (N)*

Thickness (mm)	2,00	3,00	3,50
Force (N)	744	1.240	1.584

*. Mean test value.






Maximum pull-over force (N)*

Thickness (mm)	0,50	0,60	0,70	0,80	1,00
Without washer (N)	672	800	940	1.075	1.344

*. Values obtained from the Spanish structural steel code for an ST37 sheet (350 N/mm2)





Maximum shear force (N)

Thickness (mm)	1,00	1,50
Section (mm)	1,00	1,50
Force (N)	1.183	1.735

*. Values obtained from the Spanish structural steel code for an ST37 sheet (350 N/mm2)

www.faytexsl.com
C/ Palier, 19 · 28914 Leganés (Madrid) Spain
+34 916 945 561

Translation of the Spanish version; it may contain errors.

FYT
FIJAMOS EL MUNDO

The values in table 1 are mean test values (ẋ). The following factors are recommended according to CEN/TS 17659:

Table 2 - Recommended material partial (safety) factors for fastening in structural decks of different marterials

Material of structural deck	Nominal thickness	Characteristics [a]	γM
Steel according to EN 10346	0,50 ≤ t < 0,70 mm	yield strength ≥ 280 N/mm^2	2,0
	t ≥ 0,70 mm	yield strength ≥ 280 N/mm^2	1,8
Aluminium according to EN 485	t ≥ 0,70 mm	yield strength ≥ 195 N/mm^2	2,0 [b]
Concrete according to EN 206		Minimum C12/15	2,1 [c]
Light weight concrete according to EN 12602		≥ 500 kg/m^3	3,0 [b]

Material of structural deck	Nominal thickness	Characteristics [a]	γM
Wood - soft wood according to EN 338	t ≥ 20 mm	Minimum C24	1,86 [d]
OSB according to EN 300	t ≥ 18 mm	Minimum OSC/3	1,86 [d]
Plywood according to EN 636	t ≥ 18 mm	Minimum Service class 2 (EN 1995-1-1) Intended application = Structural S	1,86 [d]

a. Recommended for new structural decks.
b. This recommended value is based on hnowledge / experience.
c. This value is based on γ_{inst} = 1,4.
d. γM is the total safety based on κ_{mod} = 0,7 according EC 5.

Example of fastener strength calculation:

Data: Aluminium purlin 3 mm / Sheet 0,6 mm / i-FYT DK3N 3,5 with washer 16

1. Tensile strength:
   - From the data sheet values:
     Wtest = 1.240 N/fastener
   - Apply 90% reduction factor:
     Wchar = 1.116 N/fastener
   - Apply safety factor:
     Wadm = 558 N/fastener

2. Pull-over resistance:
   - From the data sheet values:
     Wadm = 800 N/fastener

The lower of these values is used



Design value of the fasteners: Wadm = 558 N/fastener.

A1 REACCIÓN AL FUEGO — Fire protection
A2 — AISI 304
ALU — Drills Aluminium
Screw Self-drilling
Ph2 head
TÜV NORD PN-EN ISO 9001

Stainless

www.faytexsl.com
C/ Palier, 19 · 28914 Leganés (Madrid) Spain
+34 916 945 561

Translation of the Spanish version; it may contain errors.