Zinc-plated

FYT
FIJAMOS EL MUNDO

10111063 FYT DK1 6,3 MADERA

Material	AISI 1022 steel		Diameter (mm)	6,3
Heat treatment	Austenitising + quenching + tempering		Drilling capacity	2,5 mm.
Corrosion protection	Zinc-plated - Delta Tone	Hardness	Surface	Min 560 HV
Lengths (mm)	38 - 50		Core	240 - 425 HV
Shear failure load	9.500 N		Tensile failure load	14.000 N



Maximum pull-out force (N)*

Thickness (mm)	25	30	40	50
Force (N)	2.088	3.024	3.753	5.148

*. Mean test value.






Maximum pull-over force (N)*

Thickness (mm)	0,50	0,60	0,70	0,80	1,00
Without washer (N)	840	1.008	1.176	1.344	1.680
P 16 washer (N)	1.120	1.344	1.568	1.792	2.240
P 18 washer (N)	1.260	1.512	1.764	2.016	2.520

*. Values obtained from the Spanish structural steel code for an ST37 sheet (350 N/mm2)





Maximum shear force (N)

Thickness (mm)	0,63	0,75
Section (mm)	Timber	Timber
Force (N)	1.400	3.000

*. Values obtained from the Spanish structural steel code for an ST37 sheet (350 N/mm2)

Zinc-plated

www.faytexsl.com
C/ Palier, 19 · 28914 Leganés (Madrid) Spain
+34 916 945 561

Translation of the Spanish version; it may contain errors.

10111063 FYT DK1 6,3 MADERA

FYT
FIJAMOS EL MUNDO

The values in table 1 are mean test values (ẋ). The following factors are recommended according to CEN/TS 17659:

Table 2 - Recommended material partial (safety) factors for fastening in structural decks of different marterials

Material of structural deck	Nominal thickness	Characteristics [a]	γM
Steel according to EN 10346	0,50 ≤ t < 0,70 mm	yield strength ≥ 280 N/mm^2	2,0
	t ≥ 0,70 mm	yield strength ≥ 280 N/mm^2	1,8
Aluminium according to EN 485	t ≥ 0,70 mm	yield strength ≥ 195 N/mm^2	2,0 [b]
Concrete according to EN 206		Minimum C12/15	2,1 [c]
Light weight concrete according to EN 12602		≥ 500 kg/m^3	3,0 [b]

Material of structural deck	Nominal thickness	Characteristics [a]	γM
Wood - soft wood according to EN 338	t ≥ 20 mm	Minimum C24	1,86 [d]
OSB according to EN 300	t ≥ 18 mm	Minimum OSC/3	1,86 [d]
Plywood according to EN 636	t ≥ 18 mm	Minimum Service class 2 (EN 1995-1-1) Intended application = Structural S	1,86 [d]

a. Recommended for new structural decks.
b. This recommended value is based on hnowledge / experience.
c. This value is based on γ_{inst} = 1,4.
d. γM is the total safety based on κ_{mod} = 0,7 according EC 5.

Example of fastener strength calculation:

Data: Purlin 4 mm / sheet 0,7 mm / FYT DK1 6,3 with washer 18



1. Tensile strength:
   - From the data sheet values:
     Wtest = 3.753 N/fastener
   - Apply 90% reduction factor:
     Wchar = 3.378 N/fastener
   - Apply safety factor:
     Wadm = 1.816 N/fastener
2. Pull-over resistance:
   - From the data sheet values:
     Wadm = 1.764 N/fastener

The lower of these values is used

Design value of the fasteners: Wadm = 1.764 N/fastener.



Fire protection


Screw timber


Screw Self-drilling



Head Hexagonal



Zinc-plated

www.faytexsl.com
C/ Palier, 19 · 28914 Leganés (Madrid) Spain
+34 916 945 561

Translation of the Spanish version; it may contain errors.