# Zinc-plated

FYT
FIJAMOS EL MUNDO

## 10193P48 FYT ALAS3 4,8

| | | | | |
|---|---|---|---|---|
| Material | AISI 1022 steel | | Diameter (mm) | 4,8 |
| Heat treatment | Austenitising + quenching + tempering | | Drilling capacity | 4 mm. |
| Corrosion protection | Zinc-plated - Delta Tone | Hardness | Surface | 560 HV |
| Lengths (mm) | 25 - 45 | | Core | 240 HV |
| Shear failure load | 7.130 N | | Tensile failure load | 10.600 N |



### Maximum pull-out force (N)*

| Thickness (mm) | 1,00 | 1,50 | 2,00 | 2,50 | 2 x 0,63 | 2 x 1,00 |
|---|---|---|---|---|---|---|
| Force (N) | 1.100 | 2.000 | 2.900 | 3.800 | 1.400 | 2.500 |

*. Mean test value.







### Maximum pull-over force (N)*

| Thickness (mm) | 0,50 | 0,60 | 0,70 | 0,80 | 1,00 |
|---|---|---|---|---|---|
| Without washer (N) | 840 | 1.008 | 1.176 | 1.344 | 1.680 |
| P 16 washer (N) | 1.120 | 1.344 | 1.568 | 1.792 | 2.240 |
| P 18 washer (N) | 1.260 | 1.512 | 1.764 | 2.016 | 2.520 |

*. Values obtained from the Spanish structural steel code for an ST37 sheet (350 N/mm2)



### Maximum shear force (N)

| Thickness (mm) | 0,63 | 0,63 | 0,75 | 1,00 |
|---|---|---|---|---|
| Section (mm) | 2 x 0,63 | 2,00 | 1,50 | 2 x 1,00 |
| Force (N) | 1.800 | 2.700 | 3.200 | 3.300 |

*. Values obtained from the Spanish structural steel code for an ST37 sheet (350 N/mm2)



## Zinc-plated

www.faytexsl.com
C/ Palier, 19 · 28914 Leganés (Madrid) Spain
+34 916 945 561

Translation of the Spanish version; it may contain errors.

# 10193P48 FYT ALAS3 4,8

FYT
FIJAMOS EL MUNDO

**The values in table 1 are mean test values (ẋ). The following factors are recommended according to CEN/TS 17659:**

## Table 2 - Recommended material partial (safety) factors for fastening in structural decks of different marterials

| Material of structural deck | Nominal thickness | Characteristics [a] | γM |
|---|---|---|---|
| Steel according to EN 10346 | 0,50 ≤ t < 0,70 mm | yield strength ≥ 280 N/mm$^2$ | 2,0 |
| | t ≥ 0,70 mm | yield strength ≥ 280 N/mm$^2$ | 1,8 |
| Aluminium according to EN 485 | t ≥ 0,70 mm | yield strength ≥ 195 N/mm$^2$ | 2,0 [b] |
| Concrete according to EN 206 | | Minimum C12/15 | 2,1 [c] |
| Light weight concrete according to EN 12602 | | ≥ 500 kg/m$^3$ | 3,0 [b] |

| Material of structural deck | Nominal thickness | Characteristics [a] | γM |
|---|---|---|---|
| Wood - soft wood according to EN 338 | t ≥ 20 mm | Minimum C24 | 1,86 [d] |
| OSB according to EN 300 | t ≥ 18 mm | Minimum OSC/3 | 1,86 [d] |
| Plywood according to EN 636 | t ≥ 18 mm | Minimum Service class 2 (EN 1995-1-1) Intended application = Structural S | 1,86 [d] |

a. Recommended for new structural decks.
b. This recommended value is based on hnowledge / experience.
c. This value is based on $\gamma_{inst}$ = 1,4.
d. γM is the total safety based on $\kappa_{mod}$ = 0,7 according EC 5.

## Example of fastener strength calculation:

**Data: Steel purlin 2 mm / Sheet 0,8 mm / FYT Alas3 4,8 without washer**



1. Tensile strength:
   - From the data sheet values:
     Wtest = 2.900 N/fastener
   - Apply 90% reduction factor:
     Wchar = 2.610 N/fastener
   - Apply safety factor:
     Wadm = 1.450 N/fastener
2. Pull-over resistance:
   - From the data sheet values:
     Wadm = 1.344 N/fastener

The lower of these values is used

**Design value of the fasteners: Wadm = 1.344 N/fastener.**

A1 REACCIÓN AL FUEGO — Fire protection
Screw for Timber
Rolled beam cold-formed
Screw Self-drilling
Head Ph2

**Zinc-plated**



Translation of the Spanish version; it may contain errors.