Delta CE

FIJAMOS EL MUNDO

30113055 DELTA-FYT DK3 CE 5,5

Material	AISI 1022 steel	Diameter (mm)		5,5
Heat treatment	Austenitising + quenching + tempering	Drilling capacity		4 mm.
Corrosion protection	Delta Tone coating	Hardness	Surface	Min 560 HV
Lengths (mm)	25		Core	240 - 425 HV
Shear failure load	10.000 N	Tensile failure load		16.000 N



Maximum pull-out force (N)*

Thickness (mm)	2,00	3,00	4,00	5,00
Force (N)	3.400	6.300	9.300	11.500

*. Mean test value.




Maximum pull-over force (N)*

Thickness (mm)	0,50	0,60	0,70	0,80	1,00
Without washer (N)	840	1.008	1.176	1.344	1.680
P 16 washer (N)	1.120	1.344	1.568	1.792	2.240
P 18 washer (N)	1.260	1.512	1.764	2.016	2.520

*. Values obtained from the Spanish structural steel code for an ST37 sheet (350 N/mm2)





Maximum shear force (N)

Thickness (mm)	0,63	0,75	1,00	1,00	1,50	1,50
Section (mm)	2,00	3,00	2,00	3,00	2,00	3,00
Force (N)	3.500	5.400	6.800	7.300	10.000	10.000

*. Values obtained from the Spanish structural steel code for an ST37 sheet (350 N/mm2)



Delta CE

www.faytexsl.com
C/ Palier, 19 · 28914 Leganés (Madrid) Spain
+34 916 945 561

Translation of the Spanish version; it may contain errors.

FYT
FIJAMOS EL MUNDO

The values in table 1 are mean test values (ẋ). The following factors are recommended according to CEN/TS 17659:

Table 2 - Recommended material partial (safety) factors for fastening in structural decks of different marterials

Material of structural deck	Nominal thickness	Characteristics [a]	γM
Steel according to EN 10346	0,50 ≤ t < 0,70 mm	yield strength ≥ 280 N/mm^2	2,0
	t ≥ 0,70 mm	yield strength ≥ 280 N/mm^2	1,8
Aluminium according to EN 485	t ≥ 0,70 mm	yield strength ≥ 195 N/mm^2	2,0 [b]
Concrete according to EN 206		Minimum C12/15	2,1 [c]
Light weight concrete according to EN 12602		≥ 500 kg/m^3	3,0 [b]

Material of structural deck	Nominal thickness	Characteristics [a]	γM
Wood - soft wood according to EN 338	t ≥ 20 mm	Minimum C24	1,86 [d]
OSB according to EN 300	t ≥ 18 mm	Minimum OSC/3	1,86 [d]
Plywood according to EN 636	t ≥ 18 mm	Minimum Service class 2 (EN 1995-1-1) Intended application = Structural S	1,86 [d]

a. Recommended for new structural decks.
b. This recommended value is based on hnowledge / experience.
c. This value is based on γ_{inst} = 1,4.
d. γM is the total safety based on κ_{mod} = 0,7 according EC 5.

Example of fastener strength calculation:


Data: Steel purlin 4 mm / Sheet 0,7 mm / with screw FYT DK3 5,5 CE with washer 16



1. Tensile strength:
   - From the data sheet values:
     Wtest = 9.300 N/fastener
   - Apply 90% reduction factor:
     Wchar = 8.370 N/fastener
   - Apply safety factor:
     Wadm = 4.185 N/fastener
2. Pull-over resistance:
   - From the data sheet values:
     Wadm = 1.568 N/fastener

The lower of these values is used

Design value of the fasteners: Wadm = 1.568 N/fastener.



Fire protection · Rolled beam cold formed · Screw Self-drilling · Head Hexagonal

Delta CE